

Characteristics and Applications:

FabCO 625 is the rutile high nickel alloy flux cored wire. Applicable for Inconel 625, dissimilar welding, 5% Ni and 9% Ni plate low temperature tank welding with a good welding slag detachability, stable arc, minor spatter and good heat resistance. It has good impact toughness at -196°C, excellent corrosion resistance and oxidation resistance, especially resistance to corrosion and chloride-induced stress corrosion cracking.

Application include furnace equipment, petrochemical, power plants, marine and marine environments, LNG (liquefied natural gas) storage tank.

Notes on Usage:

1. Moisture, rust stains, oil containment on the base metal must be fully removed before welding to prevent the formation of porosity and cracks.
2. Use 80% Ar + 20% CO₂ shielding gas.
3. Keep shielding gas rate at 15-25 l/min. The best gas flow rate is 20 l/min.
4. Preheating is not required. Inter-pass temperature at 80°C~100°C.
5. Transport and storage should pay attention to moisture.

Typical Chemical Composition of Weld Metal (wt%)

	C	Mn	Si	P	S	Cr	Ni	Mo	Fe	Nb+Ta	Cu
AWS	≤ 0.10	≤ 0.50	≤ 0.50	≤ 0.02	≤ 0.015	20.0-23.0	≥ 58.0	8.0-10.0	≤ 5.0	3.15-4.15	≤ 0.50
Typical value	0.021	0.262	0.46	0.005	0.001	21.87	63.70	8.62	0.93	3.67	0.020

Typical Mechanical Properties of Weld Metal

	Yield strength MPa(ksi)	Tensile strength MPa(ksi)	Elongation %	Charpy V-Notch J (ft-lbf) -196°C (-320°F)
AWS	-	≥ 690(100)	≥ 25	-
Typical value	500(73)	790(115)	36	70(52)

Welding Position



Size and Recommended Operating Range (DC<+>)

Stick Out:15-20(mm), Flow Rate:15-25(l/min)

Position \ Diameter (mm)	1.2
F, HF	180A-200A/26V-28V
H	180A-200A/26V-28V
V-UP	130A-150A/23V-26V